



Specifications for General Purpose Polystyrene

Parameter	Value
Molecular formula	--
Mol wt	--
Cas #	[9003-53-6]
Density at 25 deg cel (g/cc)	1.039-1.041
Melt flow index at 190 deg cel (g / 10 min)	13-15
Vicat soften point (deg cel)	98 - 101

Uses:

Industry	Applications
Polymer	In mfr of cutlery, tumblers and containers In masterbatches In gloss capping materials and blending crystals